FYLONAR® www.hylomar.com

UESTO DE ESTANQUEIDAD · PÀTE D'ÉTANCHEM

HYLOMAR UNIVERSAL BLUE

NON SETTING GASKET + JOINTING COMPOUND PRODUCT SHEET

Pack sizes – 40g tube (blister card), 40g tube (carton), 100g tube (carton), 350g (cartridge).

Hylomar Universal Blue is a high performance, non-setting gasket and jointing compound. The compound is resistant to a wide range of fluids including:

- + Industrial fluids
- + Oils
- + Petroleum and synthetic diester lubricating oils
- Gasoline and kerosene
- + Water/glycol and methanol/water mixtures
- + Air + Tur
- Turbine and piston engine combustion products

Typical Applications

- Inlet manifolds
- Timing case covers
- + Gearbox and transmission components
- Thread sealing
- Water and oil pumps
- Instrument inspection covers
- Cylinder heads
- Flat rigid sumps
- Most machined surfaces
- + Gas turbines
- Water cooled generatorsTurbo vacuum systems



Hylomar Limited

Hylo House, Cale Lane, Wigan, WN2 1JT, UK | Tel: +44 (0)1942 617000 | Fax: +44 (0)1942 617001 Hylomar GmbH

Talstraße 106, 41516 Grevenbroich, Deutschland | Tel: +49 (0)2182 570 8971 | Fax: +49 (0) 2182 5708970 Hylomar LLC

158 J J Lane, Center Point, Texas 78010, USA | Tel: +1 830 634 2603

FEATURES

- Non-hardening and non-setting
- Non–flammable
- Unlimited assembly time
- + Wide operating temperature (-50°C to +250°C)
- + Allows metal to metal contact
- + Available as light, medium and heavy viscosity product
- The non-setting feature allows easy dismantling of components for service and repair work
- + Use as an non-curing thread sealant
- + Resists vibration

TYPICAL PHYSICAL PROPERTIES \diamond

Temperature range	-50°C to +250°C (-58°F to 482°F)
LIGHT GRADE	
Film Thickness	0.015 mm
Typical Surface Finish	2.0 µm Ra
Area covered by 100g	1.875m²
Product coverage after drying	2mg/cm ²
MEDIUM GRADE	
Film Thickness	0.03 mm
Typical Surface Finish	3.0 µm Ra
Area covered by 100g	1.275m²
Product coverage after drying	4mg/cm ²
HEAVY GRADE	
Film Thickness	0.09 mm
Typical Surface Finish	3.5 µm Ra
Area covered by 100g	0.56m²
Product coverage after dying	12mg/cm ²